



SEAJET 130 POLYURETHANE GLOSS VARNISH

SEAJET 130 POLYURETHANE GLOSS VARNISH is a high gloss, very hard two component varnish.

Characteristics:

- Maximum performance, two component gloss finish with ultra high gloss.
- The very tough finish is resistant to scratches and minor damage.
- Can be used on interior and exterior areas.
- Recommended for use on plywood, saloon tables and epoxy resin treated wood.
- High UV protection and resistance to abrasion, loss of gloss and chemicals.

TECHNICAL DATA

Type	Two-component polyurethane based on unsaturated polyesters.
Recommended use	As a varnish for plywoods, saloon tables, cabin soles and epoxy coated wood.

Surface Preparation	<p>Surface in poor condition: Remove old varnish layers by sanding or stripping. Existing 2-component varnish in good condition: Clean the surface. Flatten back with P60-80 abrasive paper along the grain. Then sand with abrasive paper for P100-220. Clean the surface with a tack rag. Apply a minimum of five coats of SEAJET 130 Polyurethane Gloss Varnish. Add 10-15% thinner for the first two coats. Then reduce thinning to 0-10% for further coats. Sand between coats with P280-P400 for a better finish. Clean the surface with a tack rag. Apply with a good quality bristle brush. Avoid painting varnish when damp or in direct sunlight. Dry mornings are best to paint. Mix thoroughly and stir well before use.</p>
----------------------------	---

Physical Data (Mix)	<p>Colour: Clear Flash point: 42°C Volume solids %: 50 ±2 VOC (Theoretical): 426 g/l.</p>
----------------------------	--

Application Details	<p>Mixing ratio: Base: 67 Hardener: 33 (by volume) Thinner: SEAJET THINNER P Application Data: Airspray, brush, roller* Add the hardener to the base whilst mixing. Stir well before use. Min. Temperature: 12 °C Max. humidity: 80% R.H.</p>
----------------------------	--

Spray Details	<p>Tip No.: 1.4 - 1.8 mm Paint output pressure: 3 bar Thinning: 0 - 10% (by volume)</p>
----------------------	---

Film thickness and spreading rate:	<table border="1"> <thead> <tr> <th></th> <th>Min.</th> <th>Max.</th> <th></th> </tr> </thead> <tbody> <tr> <td>Film Thickness, wet:</td> <td>60</td> <td>80</td> <td>µm</td> </tr> <tr> <td>Film Thickness, dry:</td> <td>30</td> <td>40</td> <td>µm</td> </tr> <tr> <td>Spreading Rate:</td> <td>16,7</td> <td>12,5</td> <td>m²/l (theoretical)</td> </tr> </tbody> </table>		Min.	Max.		Film Thickness, wet:	60	80	µm	Film Thickness, dry:	30	40	µm	Spreading Rate:	16,7	12,5	m ² /l (theoretical)
	Min.	Max.															
Film Thickness, wet:	60	80	µm														
Film Thickness, dry:	30	40	µm														
Spreading Rate:	16,7	12,5	m ² /l (theoretical)														

Preferable preceding coating	-
-------------------------------------	---

Preferable subsequent coating	SEAJET 130 POLYURETHANE GLOSS VARNISH
--------------------------------------	---------------------------------------

Packing	Two Pack Product
----------------	------------------

Notes	<p>* In case of brush or roller application more layers may be required to achieve the specified film thickness. The amount of thinner to be added depends on temperature of the paint and the substrate to be painted. Application by a short hair mohair or foam roller suited for polyurethanes, followed by brushing out to a smooth paint film with a soft long haired, good quality brush gives the best possible results.</p>
--------------	--


Coating data

Temperature	Drying time (at DFT 40 µ)	Overcoating interval (at DFT 40 µ)	Induction time	Pot life	Dry to launch	Remarks
-5 °C	-	-	-	-	-	-
0 °C	-	-	-	-	-	-
5 °C	-	-	-	-	-	-
10 °C	-	-	-	4 hours	-	-
20 °C	Surface dry: 2 hours Hard dry 8 hours	Min.: 24 hours Max.: 48 hours	-	3 hours	-	*
30 °C	-	-	-	2 hours	-	-

* After 48 hours light sanding with abrasive paper nr.360 is recommended.

Safety information: If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Definitions:		
Tolerances:		The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
Spreading Rate:		The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
Volume Solids:		The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697.
Overcoating Intervals:		The intervals given assume preparation consistent with good painting
Hard dry:		The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
V.O.C.:		Theoretical quantity of volatile organic compounds in g/l.

Disclaimer: Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded.

Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.